

CHANG CHUN PLASTICS CO LTD

E59481 (S)

| Mtl Dsg | Col | Min Thk mm | UL94 Flame Class | Elec | RTI Imp | Mech with w/o Imp | H W I | H A I | H V T R | D 4 9 5 | C T I | |
|---|-------|------------|------------------|-------|---------|-------------------|-------|-------|---------|---------|-------|---|
| Phenolic, "PM" furnished in the form of granules. | | | | | | | | | | | | |
| T33 | BK | 1.57 | 94HB | 150 | 150 | 150 | 0 | 0 | 4 | 7 | 4 | |
| | | 3.17 | 94V-1 | 150 | 150 | 150 | 0 | 0 | 2 | 7 | 4 | |
| | | 6.35 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 4 | 7 | 4 | |
| T353 | BK | 0.79 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 5 | 5 | 4 | |
| | | 1.57 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 3 | 5 | 4 | |
| | | 3.17 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 0 | 5 | 4 | |
| T357 | BK | 0.79 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 4 | 5 | 4 | |
| | | 1.57 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 5 | 5 | 4 | |
| | | 3.17 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 5 | 5 | 4 | |
| T614 | BN | 1.57 | 94HB | 150 | 150 | 150 | 0 | 0 | 4 | 7 | 4 | |
| | | 3.17 | 94HB | 150 | 150 | 150 | 0 | 0 | 4 | 7 | 4 | |
| | | 6.35 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 4 | 7 | 4 | |
| T359J | BK,BN | 0.79 | 94HB | 150 | 150 | 150 | 1 | 0 | 4 | 7 | 4 | |
| | | 1.57 | 94HB | 150 | 150 | 150 | 1 | 0 | 4 | 7 | 4 | |
| | | 3.17 | 94HB | 150 | 150 | 150 | 0 | 0 | 4 | 7 | 4 | |
| T373J | BK,BN | 1.00 | 94V-1 | 150 | 150 | 150 | 2 | 0 | 3 | 6 | 4 | |
| | | NC | 1.00 | 94V-0 | 150 | 150 | 150 | 2 | 0 | 3 | 6 | 4 |
| | | @ | 2.00 | 94V-0 | 150 | 150 | 150 | 1 | 0 | 3 | 6 | 4 |
| T357J | BK,BN | 0.79 | 94V-0 | 150 | 150 | 150 | 1 | 0 | 4 | 5 | 4 | |
| | | 1.58 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 4 | 5 | 4 | |
| | | 3.17 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 4 | 5 | 4 | |
| T377J | BK | 0.79 | 94HB | 150 | 150 | 150 | 2 | 0 | 4 | 7 | 4 | |
| | | 1.58 | 94HB | 150 | 150 | 150 | 1 | 0 | 4 | 7 | 4 | |
| | | 3.17 | 94HB | 150 | 150 | 150 | 0 | 0 | 4 | 7 | 4 | |
| T385J | BK,BN | 3.17 | 94V-1 | 150 | 150 | 150 | 1 | 0 | 4 | 7 | 4 | |
| | | NAT | 3.17 | 94V-0 | 150 | 150 | 150 | 1 | 0 | 3 | 7 | 4 |
| | | @ | 6.34 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 3 | 7 | 4 |
| T200NA | BK,BN | 1.00 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 0 | 7 | 4 | |
| | | 2.00 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 0 | 7 | 4 | |
| T376J | BK,BN | 1.00 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 1 | 5 | 4 | |
| | | BK | 2.00 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 1 | 5 | 4 |
| T210LA | BK | 0.80 | 94V-0 | 150 | 150 | 150 | 1 | 3 | 0 | 6 | 4 | |
| | | 1.00 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 0 | 6 | 4 | |
| | | 2.00 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 0 | 6 | 4 | |
| T389 | BK | 1.00 | 94HB | 150 | 150 | 150 | 0 | 0 | 1 | 6 | 4 | |
| | | 2.00 | 94HB | 150 | 150 | 150 | 0 | 0 | 1 | 6 | 4 | |
| | | 3.20 | 94HB | 150 | 150 | 150 | 0 | 0 | 1 | 6 | 4 | |
| T310 | BK | 1.00 | 94V-1 | 150 | 150 | 150 | 1 | 0 | 2 | 5 | 4 | |
| | | 1.58 | 94V-1 | 150 | 150 | 150 | 1 | 0 | 2 | 5 | 4 | |
| | | 3.17 | 94V-0 | 150 | 150 | 150 | 0 | 0 | 2 | 5 | 4 | |
| T308J | BK,BN | 2.00 | 94HB | 150 | 150 | 150 | 1 | 0 | 3 | 6 | 3 | |
| | | 3.17 | 94HB | 150 | 150 | 150 | 1 | 0 | 3 | 6 | 3 | |
| Urea, furnished in the form of granules | | | | | | | | | | | | |
| UM | All | 1.57 | 94HB | 100 | 100 | 100 | 0 | 0 | 2 | 6 | 1 | |