

CHANG CHUN PLASTICS CO LTD

E59481 (S)

Mtl Dsg	Col	Min Thk mm	UL94 Flame Class	Elec	RTI Imp	Mech with w/o Imp	H W I	H A I	H V T R	D 4 9 5	C T I	
Phenolic, "PM" furnished in the form of granules.												
T33	BK	1.57	94HB	150	150	150	0	0	4	7	4	
		3.17	94V-1	150	150	150	0	0	2	7	4	
		6.35	94V-0	150	150	150	0	0	4	7	4	
T353	BK	0.79	94V-0	150	150	150	0	0	5	5	4	
		1.57	94V-0	150	150	150	0	0	3	5	4	
		3.17	94V-0	150	150	150	0	0	0	5	4	
T357	BK	0.79	94V-0	150	150	150	0	0	4	5	4	
		1.57	94V-0	150	150	150	0	0	5	5	4	
		3.17	94V-0	150	150	150	0	0	5	5	4	
T614	BN	1.57	94HB	150	150	150	0	0	4	7	4	
		3.17	94HB	150	150	150	0	0	4	7	4	
		6.35	94V-0	150	150	150	0	0	4	7	4	
T359J	BK,BN	0.79	94HB	150	150	150	1	0	4	7	4	
		1.57	94HB	150	150	150	1	0	4	7	4	
		3.17	94HB	150	150	150	0	0	4	7	4	
T373J	BK,BN	1.00	94V-1	150	150	150	2	0	3	6	4	
		NC	1.00	94V-0	150	150	150	2	0	3	6	4
		@	2.00	94V-0	150	150	150	1	0	3	6	4
T357J	BK,BN	0.79	94V-0	150	150	150	1	0	4	5	4	
		1.58	94V-0	150	150	150	0	0	4	5	4	
		3.17	94V-0	150	150	150	0	0	4	5	4	
T377J	BK	0.79	94HB	150	150	150	2	0	4	7	4	
		1.58	94HB	150	150	150	1	0	4	7	4	
		3.17	94HB	150	150	150	0	0	4	7	4	
T385J	BK,BN	3.17	94V-1	150	150	150	1	0	4	7	4	
		NAT	3.17	94V-0	150	150	150	1	0	3	7	4
		@	6.34	94V-0	150	150	150	0	0	3	7	4
T200NA	BK,BN	1.00	94V-0	150	150	150	0	0	0	7	4	
		2.00	94V-0	150	150	150	0	0	0	7	4	
T376J	BK,BN	1.00	94V-0	150	150	150	0	0	1	5	4	
		BK	2.00	94V-0	150	150	150	0	0	1	5	4
T210LA	BK	0.80	94V-0	150	150	150	1	3	0	6	4	
		1.00	94V-0	150	150	150	0	0	0	6	4	
		2.00	94V-0	150	150	150	0	0	0	6	4	
T389	BK	1.00	94HB	150	150	150	0	0	1	6	4	
		2.00	94HB	150	150	150	0	0	1	6	4	
		3.20	94HB	150	150	150	0	0	1	6	4	
T310	BK	1.00	94V-1	150	150	150	1	0	2	5	4	
		1.58	94V-1	150	150	150	1	0	2	5	4	
		3.17	94V-0	150	150	150	0	0	2	5	4	
T308J	BK,BN	2.00	94HB	150	150	150	1	0	3	6	3	
		3.17	94HB	150	150	150	1	0	3	6	3	
Urea, furnished in the form of granules												
UM	All	1.57	94HB	100	100	100	0	0	2	6	1	